arXiv:cond-mat/0312639v1 [cond-mat.mtrl-sci] 25 Dec 2003

Influence of Fe and Co on Phase Transitions in Ni-Mn-Ga Alloys

Vladimir V. Khovailo,[1] Toshihiko Abe,[1] Viktor V. Koledov,[2] Minoru Matsumoto,[3] Hirokazu Nakamura,[4] Ryunosuke Note,[5] Makoto Ohtsuka,[3] Vladimir G. Shavrov,[2] and Toshiyuki Takagi[4]

[1]*National Institute of Advanced Industrial Science and Technology, Tohoku Center, Sendai 983-8551, Japan*
[2]*Institute of Radioengineering and Electronics of RAS, Moscow 125009, Russia*
[3]*Institute of Multidisciplinary Research for Advanced Materials, Tohoku University, Sendai 980-8577, Japan*
[4]*Institute of Fluid Science, Tohoku University, Sendai 980-8577, Japan*
[5]*Institute for Material Research, Tohoku University, Sendai 980-8577, Japan*

Differential scanning calorimetry (DSC) and magnetic measurements were performed to study the influence of ferromagnetic 3-*d* transition elements Fe and Co on structural and magnetic properties of ferromagnetic shape memory alloys Ni_2MnGa. Addition of Fe or Co on the Ni sites decreases the temperature of martensitic phase transition T_m, whereas addition of Co on the Mn sites results in a considerable increase of T_m. Magnetic measurement revealed that Curie temperature T_C increases upon substitution of Fe or Co for Ni. This observation is of importance for design of high temperature ferromagnetic shape memory alloys.

Keywords: quaternary Heusler alloys, martensitic transition, Curie temperature, ferromagnetic shape memory alloys

I. INTRODUCTION

In resent years ferromagnetic shape memory alloys have attracted considerable attention as a new class of actuator materials (see, for a recent review, Ref. 1). Among ferromagnetic shape memory alloys, the largest magnetic-field-induced strains arising from conversion of martensitic variants under action of a magnetic field[2,3] or caused by the shift of the martensitic transition temperature[4,5] have been observed in the most intensively studied Ni_2MnGa alloy system.

Ni_2MnGa is a representative of Mn-containing Heusler alloys. For the stoichiometric composition a structural phase transition of martensitic type from the parent cubic to a complex tetragonally based structure occurs at $T_m = 202$ K, whereas long-range ferromagnetic ordering sets at $T_C = 376$ K[6]. The martensitic transition temperature T_m was found to be very sensitive to the composition, ranging from liquid helium temperature up to over 600 K[7,8]. Contrary to T_m, Curie temperature T_C of Ni-Mn-Ga alloys is less composition dependent. Based on the published experimental results[9] it can be concluded that the highest $T_C \approx 380$ K is observed in the stoichiometric Ni_2MnGa. A decrease of T_C in the alloys with deficiency in Mn, which possesses a magnetic moment of $\sim 4\ \mu_B$, is due to the dilution of the magnetic subsystem. For the alloys with Mn excess, it was suggested that the decrease in T_C is accounted for by antiferromagnetic coupling of the extra Mn atoms[10].

Analyzing data collected for a broad compositional range of Ni-Mn-Ga alloys, Chernenko[11] pointed out that there exists a correlation between the electron concentration and stability of high-temperature β-phase in the Ni-Mn-Ga system. Now it is generally acknowledged that a change of electron concentration e/a significantly affects martensitic transition temperature T_m of Ni-Mn-Ga alloys, and, therefore, an empirical relationship between T_m and e/a can be reasonably used for the preparation of alloys with required martensitic transition temperature[12]. Since large magnetic-field-induced strains are observed only in the ferromagnetic state, an efficient control of the ferromagnetic ordering temperature is of importance for realization of this effect in a large temperature interval and development of high temperature ferromagnetic shape memory alloys. Since previous experimental studies[9,11] have shown that any deviation from the stoichiometry results in decrease of T_C in Ni-Mn-Ga alloys, we studied the influence of 3-*d* ferromagnetic transition elements Fe and Co on Curie temperature T_C and martensitic transition temperature T_m of Ni-Mn-Ga.

II. SAMPLE PREPARATION AND MEASUREMENTS

Co- and Fe-containing Ni-Mn-Ga ingots of various compositions were prepared by arc-melting of high-purity initial elements in argon atmosphere. The ingots were annealed at 1100 K for 9 days in quartz ampoules and quenched in ice water. Samples for the measurements were cut from the middle part of the ingots. The real compositions of the alloys were determined by an Inductively Coupled Plasma Mass Spectrometry (ICPMS) method. Determination of the chemical compositions by ICPMS revealed that the real compositions of the alloys are close to the nominal ones. Characteristic temperatures of the direct (martensite start, M_s and martensite finish, M_f) and the reverse (austenite start, A_s and austenite finish, A_f) martensitic transformations were determined from differential scanning calorimetry (DSC) measurements. The martensitic transition temperature T_m was calculated as $T_m = (M_s + A_s)/2$. A vibrating sample magnetometer (VSM) was used for low-field magnetic measurements. Curie temperature T_C was determined as a minimum on the temperature derivative of magnetization curve measured upon heating, dM/dT.

TABLE I: Nominal composition, martensitic transition temperature T_m and Curie temperature T_C of the alloys studied.

Nominal composition	T_m (K)	T_C (K)
$Ni_{2.13}Co_{0.03}Mn_{0.84}Ga$	318	348
$Ni_{2.10}Co_{0.06}Mn_{0.84}Ga$	315	361
$Ni_{2.07}Co_{0.09}Mn_{0.84}Ga$	306	367
$Ni_{2.16}Mn_{0.80}Co_{0.04}Ga$	345	352
$Ni_{2.16}Mn_{0.75}Co_{0.09}Ga$	437	372
$Ni_{2.16}Mn_{0.70}Co_{0.14}Ga$	525	350
$Ni_{2.16}Fe_{0.04}Mn_{0.80}Ga$	317	347
$Ni_{2.12}Fe_{0.08}Mn_{0.80}Ga$	289	358
$Ni_{2.08}Fe_{0.12}Mn_{0.80}Ga$	267	377
$Ni_{2.04}Fe_{0.16}Mn_{0.80}Ga$	223	395

Nominal compositions of the alloys studied together with their martensitic and ferromagnetic transition temperatures are given in Table 1.



FIG. 1: Temperature dependencies of magnetization M for the $Ni_{2.16}Mn_{0.84-y}Co_yGa$ alloys.

III. EXPERIMENTAL RESULTS

A. Co-containing alloys

The nominal compositions of the alloys studied are $Ni_{2.16-x}Co_xMn_{0.84}Ga$ (x = 0.03, 0.06 and 0.09) and $Ni_{2.16}Mn_{0.84-y}Co_yGa$ (y = 0.04, 0.09 and 0.14). It was found that the compositional dependencies of T_m strongly depend on the Co position. Thus, the martensitic transition temperature T_m of the $Ni_{2.16-x}Co_xMn_{0.84}Ga$ alloys slightly decreases with the Co excess, whereas in the $Ni_{2.16}Mn_{0.84-y}Co_yGa$ alloys the increase in Co content results in a significant increase of T_m (Table 1). A marked increase in the temperature of martensitic transition in the alloys where Co is substituted for Mn makes these materials attractive for use as high-temperature shape memory alloys.

The behavior of Curie temperature T_C in these two series of alloys also depends significantly on the position of Co. In the $Ni_{2.16-x}Co_xMn_{0.84}Ga$ alloys Curie temperature increases from 348 K to 367 K with increasing Co content from $x = 0.03$ to $x = 0.06$ (Table 1). Contrary to this, T_C in the $Ni_{2.16}Mn_{0.84-y}Co_yGa$ alloys exhibits a non-monotonic dependence, and initially increases from T_C = 352 K ($y = 0.04$) to T_C = 372 K ($y = 0.09$) and then decreases to T_C = 350 K for $y = 0.14$ (Fig. 1). Moreover, T_C in the $Ni_{2.16}Mn_{0.80}Co_{0.04}Ga$ alloy exhibits hysteretic feature, as evidenced from $M(T)$ measured upon heating and cooling (Fig. 2). Such an unusual behavior of ferromagnetic transition temperature is caused by the coupling of martensitic and ferromagnetic transition temperatures and has been observed in $Ni_{2.18}Mn_{0.82}Ga$ and $Ni_{2.19}Mn_{0.81}Ga$ alloys[13,14].



FIG. 2: $M(T)$ measured upon heating and cooling for the $Ni_{2.16}Mn_{0.80}Co_{0.04}Ga$ alloy.

B. Fe-containing alloys

In the Fe-containing series of Ni-Mn-Ga alloys Fe was added instead of Ni to the host $Ni_{2.20}Mn_{0.80}Ga$ composition. The nominal compositions of $Ni_{2.20-z}Fe_zMn_{0.80}Ga$ alloys are characterized by the Fe content z = 0.04, 0.08, 0.12 and 0.16. DSC measurements revealed that the martensitic transition temperature continuously decreases from T_m = 317 K to T_m = 223 K as Fe content increases from $z = 0.04$ to $z = 0.16$ (Table 1).

The low-field magnetization measurements showed that Curie temperature T_C of the $Ni_{2.20-z}Fe_zMn_{0.80}Ga$ alloys increases with the increase in Fe content (Table 1). In the sample with the highest Fe content, $Ni_{2.04}Fe_{0.16}Mn_{0.80}Ga$, T_C = 395 K is higher than that of the stoichiometric Ni_2MnGa.

IV. DISCUSSION

It was suggested that the electron concentration plays an important role not only in stabilizing the Heusler structure but that it is also a driving force for the structural phase transition in Ni_2MnGa, which takes place when the contact between the Fermi surface and Brillouin zone boundary occurs[6]. The change in a number of valence electrons results in alteration of the density of states curve, which is a basis for the correlation the extent of phase stability and electron concentration e/a[15].

Our study of Co- and Fe-containing Ni-Mn-Ga alloys revealed that increasing/decreasing in the number of conduction electron results in increase/decrease of the martensitic transformation temperature. Data presented in Fig. 3 clearly demonstrate this tendency. Resulting in decrease of the electron concentration e/a, substitution of Co for Ni as well as Fe for Ni leads to the decrease of martensitic transition temperature. In the case of substitution of Co for Mn, the increase in the electron concentration brings to the increase of T_m from 345 K for $Ni_{2.16}Mn_{0.80}Co_{0.04}Ga$ to 518 K for $Ni_{2.16}Mn_{0.70}Co_{0.14}Ga$. This result is in agreement with an earlier experimental study of Co-containing Ni-Mn-Ga alloys[16].

Therefore, these results indicate that the approach used for the description of martensitic transition temperature as a function of electron concentration in ternary Ni-Mn-Ga can also be applied for the case of quaternary Heusler alloys. Obviously, such an approach can be used only in a limited range of concentration of the forth element, where phase separation does not take place. It is worth noting, however, that new ferromagnetic shape memory alloys were found recently in Ni-Co-Ga[17] and Ni-Fe-Ga[18,19,20,21] systems, which formally can be considered as the case of complete substitution of Mn for Co and Fe, respectively.

Magnetization measurements of two series of samples where Ni was substituted by Co or Fe showed that Curie temperature increases with increasing Co (or Fe) content (Table 1). The most pronounced increase of T_C is observed in the Fe-containing alloys, where Curie temperature increases from 347 K (z = 0.04) to 395 K (z = 0.16). Note that a considerable increase in T_C was also observed in alloys where Fe was added instead of Mn, $Ni_2Mn_{1-x}Fe_xGa$[22,23]. The highest Curie temperature, T_C = 433 K, reported in those studies, was observed in the $Ni_{2.016}Mn_{0.40}Fe_{0.72}Ga_{0.864}$ composition.

The Mn content remains constant in the Fe- and Co-containing alloys (Mn content y = 0.84 for the Co-containing samples and Mn content z = 0.80 for the Fe-containing samples) and, therefore, the Mn magnetic subsystem is supposed to be not influenced by these substitutions. The observed increase of T_C in the Co- and Fe-containing samples implies that the magnetic properties of Ni-Mn-Ga should be considered taking into account small magnetic moments located on Ni atoms[24] and their coupling with magnetic moments of Mn atoms. For example, the increase in T_C in these alloys can be accounted for by a stronger Co-Mn (Fe-Mn) exchange interaction as compared to the Ni-Mn one. Our experimental data, however, are not sufficient to make an unambiguous conclusion about the mechanism responsible for the increase of T_C and therefore this effect needs further investigation. The experimentally observed increase of T_C in $Ni_{2.16-x}Co_xMn_{0.84}Ga$ and $Ni_{2.20-z}Fe_zMn_{0.80}Ga$ is in accordance with a recent theoretical consideration of magnetic properties of Ni_2MnGa and Ni_2MnAl[25]. In Ref. [25] a suggestion was made that Ni significantly affects T_C in these alloys and, therefore, Curie temperature in Ni_2MnGa could be increased by a substitution of the Ni sites. Note also that this suggestion is in accordance with empirical observation that Curie temperature of Co_2MnZ or Cu_2MnZ (Z is a non-transition element) alloys is higher than T_C in corresponding Ni_2MnZ alloys[24].



FIG. 3: Martensitic transition temperature T_m of the Fe- and Co-containing Ni-Mn-Ga alloys as a function of electron concentration e/a.

In the $Ni_{2.16}Mn_{0.84-y}Co_yGa$ alloys Curie temperature T_C exhibits a non-monotonous dependence as the Co content increases (Fig. 1). This is rather unusual, because in the Mn-containing Heusler alloys the dilution of the Mn magnetic subsystem generally results in decrease of T_C. In $Ni_{2+x}Mn_{1-x}Ga$ alloys, however, merging of T_m

and T_C is accompanied by the increase of T_C in a limited composition interval $x = 0.18 - 0.20$[26]. By analogy with the $Ni_{2+x}Mn_{1-x}Ga$ alloys it could be suggested that the increase of T_C from 352 K to 372 K as the Co content changes from $y = 0.04$ to $y = 0.09$ is accounted for by the coupling of martensitic and ferromagnetic transitions, occurring in the $Ni_{2.16}Mn_{0.75}Co_{0.09}Ga$ alloy. This is not the case, as evident from the DSC measurements, which revealed that for this composition $T_m = 437$ K is considerably higher than T_C. Therefore, it is necessary to look for another mechanism responsible for the non-monotonous compositional dependence of T_C in the $Ni_{2.16}Mn_{0.84-y}Co_yGa$ alloys. It is worth noting that similar behavior of T_C has been observed in a $Fe_2Mn_{1-x}V_xSi$ system, where Curie temperature was found to increase from 219 K to 315 K with increasing x from $x = 0$ to $x = 0.5$, followed by a rapid decrease at a higher V content[27]. It was suggested that this unusual behavior of the ferromagnetic ordering temperature in $Fe_2Mn_{1-x}V_xGa$ could be related to the band structure of the system[28]. In future it would be interesting to perform similar band calculation for the $Ni_{2.16}Mn_{0.84-y}Co_yGa$ system. Further experimental studies of $Ni_{2.16}Mn_{0.84-y}Co_yGa$ alloys are also necessary in order to determine the critical Co content at which Curie temperature has a maximal value.

V. CONCLUSION

In conclusion, our experimental results have revealed that in the studied Fe- and Co-containing Ni-Mn-Ga alloys the behavior of the martensitic transition temperature can be satisfactory described as a function of the electron concentration e/a. The magnetic measurements have shown that addition of Fe or Co instead of Ni results in increase of Curie temperature T_C. This observation together with the theoretical suggestion[25] gives a basic ground for the development of high temperature ferromagnetic shape memory alloys in the Ni-Mn-Ga system.

[1] A. N. Vasil'ev, V. D. Buchelnikov, T. Takagi, V. V. Khovailo and E. I. Estrin: Physics - Uspekhi **46** (2003) 559 - 588.

[2] S. J. Murray, M. Marioni, S. M. Allen, R. C. O'Handley and T. A. Lograsso: Appl. Phys. Lett. **77** (2000) 886 - 888.

[3] K. Ullakko, Y. Ezer, A. Sozinov, G. Kimmel, P. Yakovenko and V. K. Lindroos: Scripta Mater. **44** (2001) 475 - 480.

[4] A. A. Cherechukin, I. E. Dikshtein, D. I. Ermakov, A. V. Glebov, V. V. Koledov, D. A. Kosolapov, V. G. Shavrov, A. A. Tulaikova, E. P. Krasnoperov and T. Takagi: Phys. Lett. A **291** (2001) 175 - 183.

[5] T. Takagi, V. Khovailo, T. Nagatomo, M. Matsumoto, M. Ohtsuka, T. Abe and H. Miki: Int. J. Appl. Electromagn. Mech. **16** (2002) 173 - 179.

[6] P. J. Webster, K. R. A. Ziebeck, S. L. Town and M. S. Peak: Philos. Mag. B **49** (1984) 295 - 310.

[7] V. A. Chernenko, E. Cesari, V. V. Kokorin and I. N. Vitenko: Scripta Metal. Mater. **33** (1995) 1239 - 1244.

[8] C. Jiang, G. Feng, S. Gong and H. Xu: Mater. Sci. Eng. A **342** (2003) 231 - 235.

[9] W. H. Wang, F. X. Hu, J. L. Chen, Y. X. Li, Z. Wang, Z. Y. Gao, Y. F. Zheng, L. C. Zhao, G. H. Wu and W. S. Zan: IEEE Trans. Magn. **37** (2001) 2715 - 2717.

[10] J. Enkovaara, O. Heczko, A. Ayuela and R. M. Nieminen: Phys. Rev B **67** (2003) 212405-1 – 212405-4.

[11] V. A. Chernenko: Scripta Mater. **40** (1999) 523 - 527.

[12] X. Jin, M. Marioni, D. Bono, S. M. Allen and R. C. O'Handley: J. Appl. Phys. **91** (2002) 8222 - 8224.

[13] V. V. Khovailo, T. Takagi, J. Tani, R. Z. Levitin, A. A. Cherechukin, M. Matsumoto and R. Note: Phys. Rev. B **65** (2002) 092410-1 – 092410-4.

[14] D. A. Filippov, V. V. Khovailo, V. V. Koledov, E. P. Krasnoperov, R. Z. Levitin, V. G. Shavrov and T. Takagi: J. Magn. Magn. Mater. **258-259** (2003) 507 - 509.

[15] S. Sugimura, S. Ishida and S. Asano: J. Magn. Soc. Jpn. **25** (2001) 518 - 522.

[16] H. Nakamura, K. Tsuchiya and M. Umemoto: Trans. Mater. Res. Soc. Jpn. **26** (2001) 287 - 289.

[17] K. Oikawa, T. Ota, F. Gejima, T. Ohmori, R. Kainuma and K. Ishida: Mater. Trans. **42** (2001) 2472 - 2475.

[18] K. Oikawa, T. Ota, T. Ohmori, Y. Tanaka, H. Morito, A. Fujita, R. Kainuma, K. Fukamichi and K. Ishida: Appl. Phys. Lett. **81** (2002) 5201 - 5203.

[19] K. Oikawa, T. Ota, Y. Sutou, T. Ohmori, R. Kainuma and K. Ishida: Mater. Trans. **43** (2002) 2360 - 2362.

[20] Z. H. Liu, M. Zhang, Y. T. Cui, Y. Q. Zhou, W. H. Wang, G. H. Wu, X. X. Zhang and G. Xiao: Appl. Phys. Lett. **82** (2003) 424 - 426.

[21] Y. Li, C. Jiang, T. Liang, Y. Ma and H. Xu: Scripta Mater. **48** (2003) 1255 - 1258.

[22] Z. H. Liu, M. Zhang, W. Q. Wang, W. H. Wang, J. L. Chen, G. H. Wu, F. B. Meng, H. Y. Liu, B. D. Liu, J. P. Qu and Y. X. Li: J. Appl. Phys. **92** (2002) 5006 - 5010.

[23] G. H. Wu, W. H. Wang, J. L. Chen, L. Ao, Z. H. Liu, W. S. Zhan, T. Liang and H. B. Xu: Appl. Phys. Lett. **80** (2002) 634 - 636.

[24] P. J. Webster and K. R. A. Ziebeck: in *Landolt-Börntein New Series*, ed. By H. P. J. Wijn, (Springer-Verlag, Berlin, 1988), vol. III/19c, pp. 75 - 185.

[25] J. Enkovaara, A. Ayuela, J. Jalkanen, L. Nordström and R. M. Nieminen: Phys. Rev. B **67** (2003) 054417-1 – 054417-7.

[26] A. N. Vasil'ev, A. D. Bozhko, V. V. Khovailo, I. E. Dikshtein, V. G. Shavrov, V. D. Buchelnikov, M. Matsumoto, S. Suzuki, T. Takagi and J. Tani: Phys. Rev. B **59** (1999) 1113 - 1120.

[27] M. Kawakami: Physica B **186-188** (1993) 1037 - 1040.

[28] S. Fujii, S. Ishida and S. Asano: J. Phys. Soc. Jpn. **63** (1994) 1881 - 1888.